

Lightweight external wall insulation system incorporating thin-coat polymer render and meshcloth reinforcement

webertherm XM



Uses

- Facilitates the decoration and re-modelling of existing, tired facades
- Simplifies wall construction within the new build sector

Constraints

The quality of application of these materials depends on suitable operative skills and product familiarity.

Restrictions on weather conditions during application and curing must be respected.

Sound trade practices and printed instructions must be followed.

Good access and appropriate protection must be provided.

About this product

webertherm XM is a high performance external wall insulation system protected by meshcloth reinforced polymer renders.

webertherm XM systems when applied to a masonry substrate have BBA approval covering various types of insulation and many render finishes.

The **webertherm XM** system (using mineral fibre insulation and a suitable finish) is suitable for use on buildings over 11m. With certain finishes the system has achieved an A2 (A2, s1,D0) Reaction to fire classification in accordance with BS EN13501. Please contact Weber specification team for further details.

Technical data

webertherm XM external wall insulation systems onto masonry

Insulation Board	Reinforcement	Fixing	1st Coat	2nd Coat	Finish
Specified insulation board*	Meshcloth	Mechanical or mechanical and weberend LAC / weberend LAC rapid	weberend LAC / weberend LAC rapid	weberend PTC or N/A	weber PR310 (if required) plus decorative finish or weberwall brick

* Contact the Weber Specification team to request a specification. For use over 11m or for multi-occupancy buildings Weber only specify MFD insulation.

Features and benefits

- ▲ Provides efficient thermal insulation for refurbishment and new build projects
- ▲ Comprehensive range of colours and textures enable the creation of striking visual effects
- ▲ Has a high performance water shedding range of finishes to protect the building fabric
- ▲ Low K-value insulants allow thinner insulation to be used, or higher standards to be achieved
- ▲ Reduces interstitial condensation by creating a 'warm wall' construction
- ▲ Supported by comprehensive technical and architectural services
- ▲ BBA approved certificate no. 91/2691
- ▲ NSAI approved certificate nos. 06/0260 and 09/0338



webertherm XM

Product/system options

The following product options can be used in the **webertherm XM** system. Details on their application can be found on our website www.uk.weber, or by requesting the appropriate Data Sheet.

Product
weber CL150
weberend aid
weberend LAC
weberend LAC rapid
weberend PTC

Product
weber PR310
weberplast TF
webersil TF
webermineral TF
weberwall brick

Materials

Beads, trims and flashings

Full system beads are available in polyester powder coated galvanised mild steel, grade 304 austenitic stainless steel or aluminium in 3 m and 2.5 m lengths.

Render only beads are available in coated galvanised, stainless, coated aluminium or rigid plastic in 3 m and 2.5 m lengths.

Trims and flashings such as overcills and copings, are available in PPC aluminium in 2.5 m lengths or made to order.

Insulation

Rigid insulation boards are supplied from the following range:

EPS Expanded polystyrene – slab

Grade	SD/FRA. CFC/HCFC-free
Density	15 kg/m ³
Size	1200 x 600 mm
Thickness	30 – 200 mm

MFD Mineral fibre – slab

Grade	CFC/HCFC-free
Density	160/100 kg/m ³
Size	1200 x 600 mm
Thickness	30 – 200 mm

Meshcloth

Balanced, open weave, alkaline resistant glass fibre meshcloth is available in the following grades:

Standard duty

Weight	160 g/m ²
Mesh dimension	3.5 x 3.5 mm
Size	1m x 50m roll

Heavy duty

Weight	480g/m ²
Mesh dimension	5.5 x 5.5 mm
Size	1m x 25m roll

Fixings

When required, a wide range of fixings are available to accommodate all insulant thicknesses and substrate types. Fixings are specified on a project by project basis and pull-out values are established to ensure the EWI systems are securely fixed back to the substrate.

Undercoat

weberend LAC and **weberend LAC rapid** are factory batched for scrimming within meshcloth systems.

Top coats

Where specified, coloured polymer top coats are available for use as a background for dry-dash, or a smooth float finish for synthetic textured coatings.

Preparation

Existing rendered substrates

Hammer test and remove all areas of loose, 'bossed' render.

Treat surfaces with **weber CL150**, a biocidal wash, to remove any traces of organic growth.

Make good surface using **weberend aid**.

New build masonry or frame structure

Ensure all surfaces are clean, in-plane and of adequate thickness to provide appropriate support and stiffness without deflection or edge protrusions.

Application

Fix base and other full system beads as specified.

Fix the insulation and render only beads (if specified) as described in the System Specification Sheet or relevant project documentation.

Mix and apply **weberend LAC** or **weberend LAC rapid**, lay-in meshcloth and apply a further layer of mortar as directed.

If **weberend LAC** is used and where a synthetic finish is required, apply the relevant primer to the top coat or meshcloth coat, prior to the application of the selected textured coating.

Good practice

Do not apply:

- If frost is forecast within 24 hours of use
- In damp/wet conditions
- In temperatures below 5°C or above 30°C
- On elevations in direct sunlight or where the substrate is hot

Technical support and advice

During the planning stages of a project, advice should be sought from **Weber** technical staff.

Advice based on technical expertise together with unrivalled practical experience is freely available and covers:

Design: assistance with the selection of the appropriate system, including working details and U-value calculations.

Pre-Contract Documentation: specifications, typical details, method statements.

Contract Documentation: site packages, available through the specialist contractor. These include approved details, specification and site procedures.

To the best of our knowledge and belief, this information is true and accurate, but as conditions of use and any labour involved are beyond our control, the end user must satisfy himself by prior testing that the product is suitable for his specific application, and no responsibility can be accepted, or any warranty given by our Representatives, Agents or Distributors. Products are sold subject to our Standard Conditions of Sale and the end user should ensure that he has consulted our latest literature.

Technical services

Weber's Customer Services Department has a team of experienced advisors available to provide on-site advice both at the specification stage and during application. Detailed specifications can be provided for specific projects or more general works. Site visits and on-site demonstrations can be arranged on request.

Technical helpline

Tel: 01525 718877
 e-mail technical@netweber.co.uk

Sales enquiries

Weber products are distributed throughout the UK through selected stockists and distributors. Please contact the relevant Customer Services Team below for all product orders and enquiries.

UK and Ireland

Tel: 01525 718877
 e-mail sales@netweber.co.uk

Saint-Gobain Weber

Dickens House, Enterprise Way, Maulden Road, Flitwick, Bedford MK45 5BY, UK
 Tel: 01525 718877 e-mail: mail@netweber.co.uk www.uk.weber